

Cordenka<sup>®</sup> Growth 420 AC1

## Product Description

Compostable rayon based cellulose fiber twine  
for green house applications

## Properties

Property	Unit	Typical Value	Min	Max
Linear denisty	dtex	11.100	10.700	11.500
Breaking force	N	420	390	÷
Elongation at break	%	18,0	15,0	21,0
Yield	m / kg	900	870	935

All tests performed at cord material conditioned in standard climate (65% rel. humidity, 20 °C)  
with a cord moisture content of approx. 13%.

Material is compostable, biodegradeable and GMO free.  
Material is developed for indoor greenhouse applications.  
Material should be stored in dry conditions before use.

Development type Status 05/2021 Technical data subject to change

Manufacturer: Cordenka GmbH & Co. KG  
Industriecenter Obernburg  
63784 Obernburg, Germany  
[www.cordenka.com](http://www.cordenka.com)

# CORDENKA<sup>®</sup>

Premium Rayon Reinforcement

The data given in this document constitutes average values. The data and information given are based on our knowledge and experience to date and are not intended for use in component design, nor do they in any way constitute an implied warranty of material properties. Evaluation of the material's suitability for any specific intended application is the sole responsibility of the processor. This document supersedes all previous issues.